



CL-Technology GmbH  
Mankhauser Str.1  
P.O. Box 11 07 04  
E-mail: [CL-Technology@t-online.de](mailto:CL-Technology@t-online.de)

D- 42666 Solingen  
Phone: +49 (0) 212 38229560 – 61  
Facs: +49 (0) 212 38229562

## **CL CHROME PROTECTOR BA (FREE OF PFT, BIOLOGICAL DEGRADABLE)**

### **CHARACTERISTICS**

CL Chrome Protector BA is an anion active, environment friendly, biological degradable and PFT-free Wetting Agent which is supplied to prevent the formation of chrome acid fog during the electrolyse of chrome baths.

By simultaneous diminishing of the surface tension are also the drag-out losses clearly decreased.

CL Chrome Protector BA can be used in bright- as well as in hard chrome electrolytes. The Chrome Protector has no influence on the physical- and corrosion technical characteristics of the chrome layer.

### **APPLICATION FIELD**

Besides application of bright- and hard chrome plating, this Chrome Protector can also be used for other oxidative processes as for example etching.

### **MAKE-UP CONCENTRATION**

For 100 ltr. electrolyte are 100 - 500 ml CL Chrome Protector BA required.

### **CONSUMPTION VALUES**

For 10000 Ah are approx. 0,5 – 0,8 ltr. CL Chrome Protector BA required.

The strength of the foam layer, which is usually reached after 15 – 30 minutes with this Chrome Protector, is no standard for the efficiency of the product. For example are in chrome electrolytes with a high foreign metal impurities, hardly any formation of foam. However is efficiency of the Chrome Protector is fully given from the start of the electrolyse.

## **HAZARDOUS INDICATION**

Attention has to be paid to the legal regulations for the handling of dangerous working substances. Chemicals without a hazardous indication should not be seen as harmless.

Also with chemicals which do not require a registration, we recommend to take care and to avoid for example skin contact.

## **WARRANTY**

Seller makes no warranty, whether of merchantability, fitness or otherwise, expressed or implied, concerning the product other than it shall be of the specifications stated herein. Any recommendations made by Seller concerning the use of the product are believed to be reliable, but seller makes no warranty of the results obtained. Buyer agrees to inspect the product supplied hereunder immediately after delivery. Failure to give notice in writing as aforesaid within the specified time constitutes an unqualified acceptance of the product and a waiver of all claims with respect thereto.

08.12.06/Ri